

Sorting rules for sauna laths (Version 2017-01-01)
(referred to a ledge of 3.00 m length)

Type of wood	End splits and/or faults at the end	Splits in the middle	Knots (hard)	Resin pockets and resin galls	Blue stains and discolouration	Splint	Description
Obeche/ Ayous	Up to 8 cm	None	None	-----	Very little	-----	Light yellow – straw yellow, individually brown stains no faults, individual planning faults on the rear side are permitted, otherwise ledges to approx. 85 % fault-free on 3 sides
Aspen	Up to 8 cm	None	None	-----	Very little	-----	Light yellow - cream yellow, individual planning faults on the rear side are permitted, otherwise ledges to approx. 85 % fault-free on 3 sides